

Produkte & Technologien / Basismaterialien

SDS Standards*

Materialgruppe	Hersteller	Bezeichnung	DS/ML	TG	CTE T<Tg	CTE(50 – 260°)%	T260°	CTI UL Klasse	IPC 4101/sheet	Bemerkung
FR-4 Standard	Isola	DE 104/ML	x/x	135	60 - 70	3,5 - 4	15 - 30	2	21	
	IteQ	IT 140	x/x	140	60 - 70	3,5 - 4	15 - 30	3	21	
	NanYa	FR4-86/NP140	x/x	140	60 - 70	3,5 - 4	15 - 30	3	21	
	Panasonic	MC 100	x/x	140	60 - 70	3,5 - 4	15 - 30	3	21	
FR-4 thermostabil	Isola	IS 400	x/x	150	45	2,9	60	3	21/24/97/98/99/101	
	Panasonic	R-1566	x/x	150	40	2,4	120	1	127/92/93/94/95/122/125/128	halogenfrei, CTI 500
	NanYa	NP-155F	x/x	150	40 -60	3,5	60	3	21/24/97/98/99/101	
FR-4 Hoch-TG	Isola	IS 410	x/x	170	60	3,5	60	3	21/24/26/28/121/124/129	

*Basismaterialien mit UL Zulassung

www.storz-pcb.de