

Basismaterialien (UL zugelassen)

SDS Standards

Weitere Basismaterialien auf Anfrage

Materialgruppe	Hersteller	Bezeichnung	TG	CTE T<Tg	CTE(50 – 260°)%	T260°	CTI UL Klasse	IPC 4101/sheet
FR-4 Standard	Isola	DE 104/ML	135	60 - 70	3,5 - 4	15 - 30	2	21
	NanYa	FR4-86/NP140	140	60 - 70	3,5 - 4	15 - 30	3	21
	Wazam	H140 A	140	50-70	4,3		3	21
	Wazam	H 1600A*	135	60	4,2		0	97
FR-4 thermostabil	Isola	IS 400	150	45	2,9	60	3	21/24/97/98/99/101
	Panasonic*	R-1566	150	40	2,4	120	1	127/92/93/94/95/122/125/128
	NanYa	NP-155F	150	60	3,5	60	3	21/24/97/98/99/101
	ITEQ	IT-158	150	40	3,3	60	3	99/101
	Wazam	H150(LF)	150	55	3,3	30	3	99
	Wazam	H1170	180	45	2,9	60	3	126

* halogenfrei, CTI 500